

Memory Foam GB 55M (VC50/55)



This high-quality Memory Foam is perfect for adding an extra level of comfort and support to any mattress.

CHARACTERISTIC	SPECIFICATION	TEST METHOD
AVERAGE NET PIECE DENSITY	47.5-52.5 Kgm ³	BS EN ISO 845 : 2009 (ISO 845: 2006)
NOMINAL HARDNESS	47-63N	BS EN ISO 2439: METHOD B 2008
TENSILE STRENGTH	50Kpa min	BS EN ISO 1798: 2008
ELONGATION @ BREAK	100% min	BS EN ISO 1798: 2008
RECOVERY TIME	<20	IN HOUSE TEST
FORCE AFTER 25% INITIAL HOLD	80N	IN HOUSE TEST
FORCE AFTER 65% HOLD	210N	IN HOUSE TEST
FORCE AFTER 25% HOLD RETURN	40N	IN HOUSE TEST
COMP MODULUS	3	IN HOUSE TEST
25% HYSTERESIS LOSS	17	IN HOUSE TEST

NOTE: THE FOAM COMPLIES WITH THE FURNITURE AND FURNISHINGS (FIRE) (SAFETY) REGULATIONS, 1988 S.I. No 1324 SCHEDULE 1 PART 1, (AMD 1989, 1993 and 2010)



Why Choose GB Foam Direct?

GB Foam has been supplying high-quality foam products for more than 40 years. All our products are created to the highest standard, using the very best materials and the most advanced cutting equipment.

We pride ourselves on the exceptional quality of our foam products and hold product safety in the highest regard. Everything we produce is created to ISO 9001 standards and exceeds the threshold for UK Fire Safety regulations. Our foam is put through vigorous flammability tests to guarantee the safety of you and others around you.

Our UK based factory is equipped with some of the most advanced foam cutting technology currently available and our professional foam cutters are some of the best in the industry. Many have been a part of GB Foam for over a decade.

From manually controlled band and tilt knife cutting to intrinsic computer operated CNC Routing and CAD Design, GB Foam has everything you'll need to achieve the perfect foam product.

To purchase this grade of foam cut to size visit: www.gbfoamdirect.co.uk

For trade enquiries visit: www.gbfoam.co.uk